

A highly fluid epoxy grout for dynamic/ repetitive load applications gap width between up to 10mm

Uses

Conbextra EP10 is a low viscosity epoxy grout for situations where heavy dynamic or mobile loads are encountered. It is ideal for grouting in small gaps between a base plate and substrate which needs filling and the structural load be uniformly distributed. Typical applications are reciprocating machinery, testing equipment, heavy crane and transporter rails, high speed turbines, centrifuges and drop forges.

Also for use in conditions where chemical spillage may be encountered. Typical situations could be met in steelworks, refineries, electroplating works and chemical plants.

Due to the low viscosity of Conbextra EP10 it can be used to fill hairline cracks in concrete slabs from 0.25mm and larger on horizontal surfaces using a gravity fed method. Using suitable equipment, Conbextra EP10 can also be used to pressure inject cracks down to 0.10mm.

Advantages

- High compressive, tensile and flexural strengths
- Resistant to repetitive dynamic loads
- Fast, convenient installation with early strength gain
- Withstands a wide range of chemicals
- Non-shrink and hence ensures complete surface contact and bond
- Low creep characteristics under sustained loading

Description

Conbextra EP10 is a two component low viscosity epoxy system for grouting gaps up to 10 mm and crack injection.

Technical Support

Parchem offers a comprehensive range of high quality, high performance construction products. In addition, Parchem offers technical support and on-site service to specifiers, end-users and contractors.

Chemical Resistance

Conbextra EP10 is resistant to oil, grease, fats, most chemicals, mild acids and alkalis, fresh and sea water. Consult Parchem Technical Services when exposure to solvents or concentrated chemicals is anticipated.

Properties

The following results are typical for the hardened grout at 20°C.

Test method for:	Typical result EP10
Density (kg/m³):	1060
Viscosity	
@ 10°C:	250 - 450 cps
@ 20°C:	150 - 200 cps
@ 30°C:	50 - 100 cps
Compressive strength (MPa)	
1 day:	57
3 days:	66
7 days:	83
Indirect Tensile strength @ 7 days (AS1012.10-2000)	15 MPa @ 23°C
Modulus of Rupture @ 7 days (Flexural Strength) (AS 1012.11-2000)	30 MPa @ 23°C

Note: Compressive strengths stated above were measured using cube samples. Test results obtained will vary if testing is carried out to an alternative standard or sample dimensions are used.

Pot life

Ambient temperature affects the time for which bulk material will remain fluid.

Typical values in minutes are:

	10°C	20°C	30°C	40°C
Pot Life	40	20	10	-

Exotherm

All epoxy systems will develop a temperature rise on mixing. Its extent will be a function of the volume to surface ratio, the ambient temperature, as well as the mass and thermal conductivity of the surrounding materials. Contact Parchem for specific data on each product.

Specification Clause

Performance specification

All epoxy resin grouting where shown on the drawings must be carried out with a factory packed product. The hardened grout must have a compressive strength which exceeds 80 MPa at 7 days, a tensile strength which exceeds 15 MPa at 7 days and a flexural strength which exceeds 28 MPa at 7 days.

The storage handling and placement of the grout must be in strict accordance with the manufacturer's instructions.

Fosroc®

Conbextra EP10

Instructions for Use

Foundation surface

All contact surfaces must be free from oil, grease, free standing water or any loosely adherent material. Concrete surfaces should be cut back to a sound base. All dust must be removed and bolt holes or fixing pockets blown clean of any dirt or debris.

Steel surfaces

All steel surfaces should be shot blasted free of rust, paint and flaky mill scale.

Formwork

The formwork should be constructed to be leakproof as Conbextra EP10 is a free flowing grout. Loss of grout once the material is placed, but not hardened, will result in incomplete filling of the gap.

For free flow grout conditions it is essential to provide a hydrostatic head of grout. To achieve this a feeding hopper system should be used.

Forming materials should be coated with a release agent such as grease or wax material or a plastic coating. These coatings act as a bond breaker so that a smooth grout surface is achieved after form removal and the forms are protected for reuse.

Mixing

Pour all the contents of the hardener pack into the base container. Mix using a slow speed power mixer until homogeneous.

For all products, mix using a slow speed power mixer for two minutes or until a uniform colour is achieved in the grout.

Placing

The mixed grout should be poured steadily from one side only to eliminate the entrapment of air.

Continuous grout flow is essential.

Sufficient grout must be available prior to starting.

The time taken to pour a batch should be regulated to the time taken to prepare the next batch.

With the smaller 300ml kit size a nozzle is provided so that when mixed can be squeezed or poured into small gaps or hairline cracks above 0.25mm.

Please refer to the Conbextra Epoxy Grouts Application Guide for further information. This is available from the website or your local Parchem branch.

Important notice

A Safety Data Sheet (SDS) and Technical Data Sheet (TDS) are available from the Parchem website or upon request from the nearest Parchem sales office. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.



constructive solutions

*Manufactured and sold under license from Fosroc International Limited. Fosroc and the Fosroc logo are trade marks of Fosroc International Limited, used under license. *Denotes a trade mark of Fosroc International Limited.

Page 2

Flow characteristics

The maximum distance of flow is governed by the gap thickness, the head of grout applied and the ambient temperature.

Cleaning

All tools and equipment should be cleaned immediately after use with Fosroc Solvent 10. Spillages should be absorbed with sand or sawdust and disposed in accordance with local regulations.

Temperature

During application

Conbextra EP10 grouting may be carried out without special precautions at ambient temperatures from 5°C - 25°C.

In service

Conbextra EP10 is resistant to frost and sub zero temperatures. It is also suitable in service up to 45°C.

Estimating

Supply

Conbextra EP10: 2 component packs

Conbextra EP10 300ml Pack	FC523120-300ML
Conbextra EP10 1.5L Pack	FC523120-1.5L
Conbextra EP10 Hardener of 15L pack	FC523124-5L
Conbextra EP10 Base of 15L pack	FC523125-10L

For further information on any of the above, please consult with your local Parchem sales office.

Shelf Life

Conbextra EP10 has a shelf life of 3 years from date of manufacture if kept in a dry, cool store in the original, unopened bags or packs. Refer to the Use by Date indicated on the packaging.



Parchem Construction Supplies Pty Ltd
7 Lucca Road, Wyong NSW 2259
Phone: 1300 737 787
www.parchem.com.au
ABN 80 069 961 968

Distributed in New Zealand by: Concrete Plus Ltd
23 Watts Rd, Sockburn 8042 Ph: 03 343 0090