



Fosroc® Concure X90

Promotes efficient cement hydration, minimises shrinkage whilst increasing durability of the concrete surface

Uses

Concure X90 is suitable for curing all freshly laid concrete either smooth or textured, indoors or outdoors.

Advantages

- Complies with Australian Standards AS3799
- Achieves water retention of 90% or greater
- Increased abrasion resistance
- Contains no wax
- Eliminates the need for curing by ponded water, damp hessian or polythene sheeting
- Reduces concrete dusting
- Reduces plastic shrinkage
- One coat application
- Equipment washable in water
- Can have red fugitive dye added

Due to its unique formulation and blend of resins, Concure X90 will begin to break down after 7 days and, if applied at the specified application rates, will totally oxidise and leave the surface, subject to uv exposure, within 45 - 55 days of the application. This reduces the need for surface cleaning in preparation for after trades.

Description

Concure X90 is a blend of resins and surfactants emulsified in water and is specially formulated to cure freshly laid concrete. The impervious film formed by Concure X90 prevents excessive water evaporation, promotes efficient cement hydration, minimises shrinkage whilst increasing durability of the concrete surface.

Technical Support

Parchem offers technical support to specifiers, end-users and contractors, as well as on-site technical assistance.

Properties

Data quoted typical for this product, but does not constitute a specification.

Appearance:	Milky homogenous liquid or with red fugitive dye
Volume solids:	49% ± 1%
Drying time:	
Tack free:	1 - 3 hours
Hard dry:	4 - 8 hours
Trafficable:	24 hours
Application temperature:	10°C - 35°C
Flashpoint:	84°C
Viscosity:	0.22 pascal seconds
Solubility in water:	Soluble

Application Instructions

Surface application

Apply Concure X90 to the concrete as soon as the bleed water has gone and the new concrete has hardened sufficiently so as not to be marked by the application process.

Apply Concure X90 undiluted at a rate of 1 litre per 5 .

Best applied by spray, however, may also be applied by brush, roller or broom.

Cleaning

Concure X90 should be removed from tools and equipment with water.

Estimating

Supply

900804	20 litre
900801	205 litre
900802	1000 litre totes

Coverage

Concure X90:	5m ² per litre
---------------------	---------------------------

Shelf life

12 months if kept in a dry store in original, unopened packs.

Storage Conditions

Store in cool, dry conditions, away from sources of heat and naked flames, in the original, unopened packs. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced.

Fosroc® Concure X90

Important notice

A Safety Data Sheet (SDS) and Technical Data Sheet (TDS) are available from the Parchem website or upon request from the nearest Parchem sales office. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.



*Manufactured and sold under license from Fosroc International Limited. Fosroc and the Fosroc logo are trade marks of Fosroc International Limited, used under license. *Denotes a trade mark of Fosroc International Limited.

constructive solutions



Parchem Construction Supplies Pty Ltd
7 Lucca Road, Wyong NSW 2259
Phone: 1300 737 787
www.parchem.com.au
ABN 80 069 961 968

Distributed in New Zealand by: Concrete Plus Ltd
23 Watts Rd, Sockburn 8042 Ph: 03 343 0090