

Seasoning New Forms

Seasoning instructions

USES

1. Power wash all new forms with warm water and a commercial grade detergent to remove mill oil/grease.
2. Conlift Aluminium Seasoner works best when air temperature and form temperature is above 21°C.
3. Spray product on side rails while forms are still in stacks.
4. Lay forms on ground, face sheets up.
5. Apply Conlift Aluminium Seasoner with a 12mm or 20mm nap roller. An 450mm wide roller works best.
6. Uniform bubbling on the form surface indicates that the product is properly reacting with the aluminum. Average reaction time is 20 minutes to 1 hour, depending on air and form surface temperature. Do not allow Conlift Aluminium Seasoner to dry on the form; lightly mist with water if necessary. Once bubbling has stopped, the aluminum will be dull and almost grey in color.
7. Remove product with a water hose. Do not use a high pressure washer. Be careful not to disrupt the newly formed oxides on the form surface. Once these oxides dry, they will be well bonded to the surface.
8. Allow forms to dry completely.

Following these instructions will help on your first few pours. However, even under the best conditions you will have some reaction with the first pour being the worst. Try to plan your first pour on new aluminum forms where most of the wall will be hidden.

Seasoning Instructions



ADDITIONAL INFORMATION

Parchem provides a wide range of complementary products which include:

- concrete repair – cementitious and epoxy
- grouts and anchors – cementitious and epoxy
- waterproofing membranes – liquid applied, cementitious and bituminous sheet membranes
- waterstops – pvc and swellable
- joint sealants – building, civil and chemical resistant
- industrial flooring systems – cementitious and epoxy
- architectural coatings
- filler boards – swellable cork, bituminous and backing rod
- ancillary products

For further information on any of the above, please consult with your local Parchem sales office.

IMPORTANT NOTICE

A Material Safety Data Sheet (MSDS) and Technical Data Sheet (TDS) are available from the Parchem website or upon request from the nearest Parchem sales office. Read the MSDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

PRODUCT DISCLAIMER

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.



PARCHEM	TILT UP		
SEASONING INSTRUCTIONS	JANUARY 10		
www.parchem.com.au	7 Lucca Road, Wyong NSW 2259	Phone 1300 737 787	ABN 80 069 961 968