

Nitomortar ELS

Spray-applied, trowel finished, high build, chemical and abrasion resistant epoxy liner system - (2 mm to 20 mm thickness)

USES

A sprayable epoxy mortar with maximum chemical and abrasion resistance for the protection of concrete and similar substrates. Ideal for rehabilitation of manholes, lining of outfalls, sewers and similar structures.

Nitomortar ELS is simple and cost effective for overhead, vertical and horizontal resurfacing lining to both dry and damp surfaces. The low odour, non-sag, and chemical resistant properties of Nitomortar ELS make the ideal material for long lasting manhole wall rehabilitation, lining of large diameter pipes, and sewers.

Nitomortar ELS can be used in brick, block and precast concrete manholes. Nitomortar ELS provides a permanent impermeable, high strength, monolithic lining to the interior of manhole walls.

ADVANTAGES

- Resistant to a wide range of acids, alkalis and industrial chemicals
- Resistant to biological attack
- Superior chemical and physical bond to virtually all substrates, dry or damp
- No need for priming concrete surfaces, therefore cutting labour costs and reducing risk of bad priming
- Prepacked for ease of mixing
- 100% solids content - contains no solvent
- Strengths in excess of most concrete substrates to which material is applied. Excellent resistance to abrasion and impact
- Cured material provides a long lasting waterproof barrier
- Unaffected by freeze-thaw attack
- Potable water approved - AS/NZS 4020:2005

DESCRIPTION

Nitomortar ELS is a solvent free, two component system consisting of epoxy resins and chemicals, incorporating a special blend of chemical resistant fillers. The two components increase their gel structure upon mixing, and thereby form a superior chemical and abrasion resistant lining material with no sagging of the gelled product.

TECHNICAL SUPPORT

Parchem offers a comprehensive range of high performance, high quality concrete repair and construction products. In addition, the company offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance.

DESIGN CRITERIA

Nitomortar ELS is spray applied generally in layers between 2 mm and 5 mm per layer - the minimum total thickness should be 2 mm. Maximum thickness will depend on the particular project requirements, however thickness of up to 20 mm can be achieved in multiple layers.

Consult your Parchem sales office for further details.

PROPERTIES

The following results are typical for the product but do not constitute a specification.

COMPRESSIVE STRENGTH

28 days:	40 MPa
Pot life:	1 hour @ 25°C
Initial hardness:	4 hours @ 25°C
Minimum "back to service" time:	6 hours @ 25°C
Full cure:	7 days @ 25°C
Adhesion to concrete:	>1 MPa substrate failure

Note: Cure times will increase by a factor of 2 for each 10°C reduction in temperature.

MINIMUM APPLICATION

Temperature:	5°C
---------------------	-----

CHEMICAL RESISTANCE:

Performance of Nitomortar ELS blocks continually immersed at 23°C for 28 days:

Bleach		Excellent
Detergent		Excellent
Sodium hydroxide	25%	Excellent
Diesel fuel/petrol	100%	Excellent
Sulphuric acid	50%	Excellent
Nitric Acid		Colour Change
	25%	Excellent
Phosphoric Acid	25%	Excellent
Hydrochloric Acid	25%	Excellent
Toluene	100%	Excellent
Kerosene	100%	Excellent

APPLICATION INSTRUCTIONS

PREPARATION

Clean the surface and remove any dust, unsound concrete, oil, paint, grease, corrosion deposits or algae. Roughen the surface and remove any laitance by light scabbling or grit-blasting. Where possible, saw cut or cut back the extremities of the repair locations to a depth of 3 mm to avoid feather-edging and to provide a square edge.

Prior to application of Nitomortar ELS all active hydrostatic leaks must be stopped by the use of Vandex Plug, a rapid setting mortar.

MIXING

Nitomortar ELS is supplied in the correct proportions to facilitate easy on-site mixing. A slow speed electric drill with a suitable paddle can be used for efficient mixing. Satisfactory mixing can be achieved by thoroughly mixing all contents of the base resin and hardener component in the original container. Mix continuously for approximately 3 minutes until a uniform consistency has been reached.

APPLICATION

Nitomortar ELS is spray applied using specialised equipment and contractors are advised to carry out trials prior to proceeding with any contract. Advice on suitable application equipment and application method is available on request from your nearest Parchem sales office.

To avoid sagging on overhead surfaces, do not apply Nitomortar ELS greater than 5 mm per layer. If a smooth surface is required, close the surface with a steel trowel.

Note: do not thin components as solvents will prevent proper cure.

Nitomortar ELS should be applied only when the substrate temperature and the ambient temperature is above 5°C.

Do not attempt to mix part packs as incorrect proportioning can severely affect the cured properties of the product.

CLEANING

Nitomortar ELS should be removed from tools, equipment and mixers with Solvent 10 immediately after use.

LIMITATIONS

Nitomortar ELS should not be used when the temperature is below 5°C and falling. Do not mix part packs under any circumstances. The ambient and substrate temperatures will affect the spray application and product film build characteristics. If any doubts arise concerning temperature or substrate conditions, consult your local Parchem sales office.

ESTIMATING

SUPPLY

Nitomortar ELS: 16 litre pack

Solvent 10: 4 and 20 litre cans

COVERAGE

Nitomortar ELS: 8.0 m²/ 16 litre pack at 2 mm thick
3.2 m²/ 16 litre pack at 5 mm thick

Notes: The coverage figures for Nitomortar ELS are theoretical - due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.

STORAGE

SHELF LIFE

All products have a shelf life of 12 months at 20°C if kept in a dry store in the original, unopened packs.

STORAGE CONDITIONS

Store below 35°C in dry conditions in the original, unopened packs.

ADDITIONAL INFORMATION

Parchem provides a wide range of complementary products which include:

- concrete repair – cementitious and epoxy
- grouts and anchors – cementitious and epoxy
- waterproofing membranes – liquid applied, cementitious and bituminous sheet membranes
- waterstops – pvc and swellable
- joint sealants – building, civil and chemical resistant
- industrial flooring systems – cementitious and epoxy
- architectural coatings
- filler boards – swellable cork, bituminous and backing rod
- ancillary products

For further information on any of the above, please consult with your local Parchem sales office.

IMPORTANT NOTICE

A Material Safety Data Sheet (MSDS) and Technical Data Sheet (TDS) are available from the Parchem website or upon request from the nearest Parchem sales office. Read the MSDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

PRODUCT DISCLAIMER

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.

*Manufactured and sold under license from Fosroc International Limited. Fosroc and the Fosroc logo are trade marks of Fosroc International Limited, used under license. *Denotes a trade mark of Fosroc International Limited.